

Qingdao Kangdeli Industrial and Trading Co.,Ltd

Color	Thick mm	Visible light		Sunlight		Shading coefficient (SC)	Sum of transmittance of solar energy
		Transmittance	Reflection	Direct transmittance	Direct reflection		
Euro Bronze Ref.	5	27.00	50.00	33.00	35.00	0.47	41.00
	6	26.00	52.00	31.00	36.00	0.44	39.00
Golden Bronze Ref.	5	25.20		31.50		0.37	39.46
Pink Ref.	4	30.66	36.06	47.82	29.17	0.60	53.76
	6	29.92	28.64	46.40	22.14	0.61	54.52
Euro Grey Ref.	4	26.90	19.59	37.38	17.36	0.55	49.05
	6	19.55	13.99	27.64	12.96	0.48	42.97
Dark Grey Ref.	4	17.96	10.10	30.09	11.30	0.51	45.21
	5	14.03	9.07	25.06	10.65	0.47	42.05
	6	13.02	6.97	22.70	8.20	0.46	40.53
Blue Grey Ref.	5	27.76	45.54	34.25	32.37	0.48	42.87
	6	26.95	38.61	31.69	27.65	0.47	42.18
French (Light) Green Ref.	5	31.12	34.80	25.49	19.62	0.45	39.65
	6	29.94	33.72	21.12	18.92	0.41	36.59
Dark Green Ref.	5	28.55	26.00	37.62	17.87	0.35	49.14
Ford Blue Ref.	5	27.50	19.38	37.07	16.56	0.55	49.03
	6	24.97	16.51	32.04	14.72	0.51	45.78
Dark Blue Ref.	4	25.62	13.98	39.36	16.47	0.57	50.76
	5	20.92	13.52	33.42	15.00	0.53	46.73
	6	13.42	13.68	25.52	16.81	0.45	40.40
Clear Silver Ref.	5	50.58	34.10	58.00	25.85	0.70	61.89
	6	42.75	30.11	52.31	28.29	0.64	56.99
Clear Crystal Blue Ref.	6	76.00		69.00		0.84	75.00
Clear Pearl Blue Ref.	6	67.80		61.15		0.75	67.98

Coated Off-Line(Soft Coated) Glass: Tempered Not Acceptable.

Color	Thick mm	Visible light		Sunlight		Shading coefficient (SC)	Sum of transmittance of solar energy
		Transmittance	Reflection	Direct transmittance	Direct reflection		
Clear silver grey soft coated T6	4.5	6.70				0.07	IR Rej: 94.4
Clear silver grey soft coated T13	6	14.2	29.67			0.22	U Value:6.25
	8	14.03	29.87			0.21	U Value:6.24
Ocean blue red soft coated	5	2.50				0.03	IR Rej: 96.7
Ford blue red soft coated	5	2.20				0.02	IR Rej: 99.1

Dark blue red soft coated	5	2.10				0.02	IR Rej: 98.3
Dark green red soft coated	5	2.80				0.03	IR Rej: 98.1
Coated Off-Line(Soft Coated) Glass: Tempered Acceptable.							
Color	Thick mm	Visible light		Sunlight		Shading coefficient (SC)	Sum of transmittance of solar energy
		Transmittance	Reflection	Direct transmittance	Direct reflection		
Clear golden soft coated	5/6	28.00	39.70	26.00	23.00	0.31	34.50
Clear silver soft coated T8	5/6	8.00	40.00	12.00	33.00	0.23	14.00
Clear silver soft coated T14	5/6	14.00	24.00	15.00	30.00	0.29	16.00
Clear silver soft coated T20	5/6	20.00	25.00	17.00	25.00	0.35	18.00
Clear silver soft coated T30	5/6	30.00	18.00	24.00	24.00	0.45	25.00
Clear silver soft coated T40	5/6	40.00	12.00	28.00	18.00	0.51	30.00
Clear blue grey soft coated T50	5/6	50.00	13.00	42.00	16.00	0.64	45.00
Clear blue grey soft coated T60	5/6	60.00	17.00	55.00	11.00	0.75	57.00
Clear blue grey soft coated T70	5/6	70.00	21.00	65.00	16.00	0.83	68.00
Clear soft coated T80	5/6	80.00	20.00	75.00	15.00	0.84	78.00